

**Mansol (Preforms) Limited**  
1 Hollands Road, Haverhill  
Suffolk, CB9 8PX, England

Tel: (01440) 702371  
Fax: (01440) 712512  
E-mail: [info@mansol-preforms.com](mailto:info@mansol-preforms.com)  
Web: [www.mansol-preforms.com](http://www.mansol-preforms.com)  
Registered in England No: 536059

**GLASS DATA SHEET - L13**

Code :		L13
Coefficient of Expansion x 10 <sup>-7</sup> cm/cm/°C (30°C - 300°C) :		75
Dielectric Constant (1MHz @ 25°C) :		71
Volume resistivity Log (Ω-cm)	50°	9.8
	150°	7.0
Softening Point °C		278
Density g/cm <sup>2</sup>		7.57
Sealing Temperature °C		320
Colour		Dark Green

**COMPANY CONFIDENTIAL**

This document and information contained herein is communicated in confidence, neither the whole nor any extract may be disclosed, loaned copied or used for manufacturing or tendering purposes without the consent of Mansol (Preforms) Ltd.