

Mansol (Preforms) Limited
1 Hollands Road, Haverhill
Suffolk, CB9 8PX, England

Tel: (01440) 702371
Fax: (01440) 712512
E-mail: info@mansol-preforms.com
Web: www.mansol-preforms.com
Registered in England No: 536059

GLASS DATA SHEET - MSoft7

Code :	MSoft7
Specific Gravity (at 20°C) :	2.65
Coefficient of Expansion x 10 ⁻⁶ cm/cm/°C (30°C - 300°C) :	13.0
Softening Point	486C
Working Temp.	750C
Melt flow index	82

COMPANY CONFIDENTIAL

This document and information contained herein is communicated in confidence, neither the whole nor any extract may be disclosed, loaned copied or used for manufacturing or tendering purposes without the consent of Mansol (Preforms) Ltd.