

Mansol (Preforms) Limited

1 Hollands Road, Haverhill
Suffolk, CB9 8PX, England

Tel: (01440) 702371

Fax: (01440) 712512

E-mail: info@mansol-preforms.com

Web: www.mansol-preforms.com

Registered in England No: 536059

GLASS DATA SHEET - MSOFT 6

Code : MSOFT6

Specific Gravity (at 20°C) :

Coefficient of Expansion x 10⁻⁷ cm/cm/°C (30°C - 300°C) : 11.5 x 10⁻⁶

Softening Point

Sealing Temperature 700-750

COMPANY CONFIDENTIAL

This document and information contained herein is communicated in confidence, neither the whole nor any extract may be disclosed, loaned copied or used for manufacturing or tendering purposes without the consent of Mansol (Preforms) Ltd.