

**Mansol (Preforms) Limited**  
1 Hollands Road, Haverhill  
Suffolk, CB9 8PX, England

Tel: (01440) 702371  
Fax: (01440) 712512  
E-mail: [info@mansol-preforms.com](mailto:info@mansol-preforms.com)  
Web: [www.mansol-preforms.com](http://www.mansol-preforms.com)  
Registered in England No: 536059

**GLASS DATA SHEET - MSOFT9**

Code :	MSOFT9
Specific Gravity (at 20°C) :	6.70
Coefficient of Expansion x 10 <sup>-6</sup> cm/cm/°C (25-260°C) :	12.0x10 <sup>-6</sup>
Working Temp.	380°C
Softening Point	340°C
Transformation Point	285°C

**COMPANY CONFIDENTIAL**

This document and information contained herein is communicated in confidence, neither the whole nor any extract may be disclosed, loaned copied or used for manufacturing or tendering purposes without the consent of Mansol (Preforms) Ltd.